

## **Oxirein JV-112**

---

<b>Type</b>	Red pigment
<b>Delivery form</b>	Powder
<b>Chemical class</b>	Synthetic iron oxide $\alpha$ -Fe <sub>2</sub> O <sub>3</sub>
<b>Colour index</b>	Red pigment 101

### **Specification**

### **Colour values and tinting strength**

Reference	Oxirein JV-112		
Full shade	$\Delta L$	min. -0.5	max. 0.5
	$\Delta a$	min. -1.0	max. 1.0
	$\Delta b$	min. -1.3	max. 1.3
	$\Delta E_{ab}$		max. 1.5
Relative tinting strength		min. 95%	max. 105 %

### **Technical data**

	Water-soluble content		max. 0.45 %
	Sieve residue (0.045 mm. sieve)		max. 0.06 %
	PH	min. 4.5	max. 7.5
<b>Informative technical data</b>	Fe <sub>2</sub> O <sub>3</sub>	min. 94 %	max. 97 %
	SiO <sub>2</sub> + Al <sub>2</sub> O <sub>3</sub>		max. 4.0 %
	Loss on ignition at 1,000° C, ½ h		max. 0.8 %
	Moisture content		máx. 0.5 %
	Particle shape	Spherical	
	Predominant particle size		max. 0.09 µm
	Oil absorption	approx. 28 g/100 g	
	Tamped density	min. 0.7 g/ml	max. 1.2 g/ml
	Density	approx. 5.0 g/ml	

### **Packaging**

25 Kgs. sacks or 1Mt big bags. Other packaging available on demand.

### **Transport and storage**

Protect against weathering. Store in a dry room and avoid extreme fluctuations in temperature. Sacks must be closed after opening in order to avoid moisture and contamination absorption.

### **Safety measures**

This product is not classified as dangerous neither under the relevant EC Directives nor under local regulations in the EU member states..